

DENKA SC-1

Amorphous Calcium Aluminate-Based Quick Hardening Additive

Description

DENKA SC-1 is an amorphous calcium aluminate-based accelerator used to achieve rapid setting times and high early strength in mortar and cement.

Features

- Handling time can be adjusted to between 10 minutes and 1 hour by using general setting modifiers such as tartaric acid or dedicated setting modifier DENKA SETTER D-200
- Excellent initial strength (10~30MPa can be achieved in 3 hours)
- Excellent crack resistance
- Reduced self-shrinkage and drying shrinkage due to expansion characteristics

Applications

- Self-leveling mortar
- Non-shrink grout
- Tile adhesive mortar
- Repair/rendering mortar
- Dry process shotcrete

Packaging

- 20kg paper bags
- 1000kg bulk bags

Shelf Life

- 12 months from production date
- Determine the production date by reference to the lot number. A lot number of "1AXXX" corresponds to production in Jan 2001; "2BXXX" to Feb 2002 and so on.

Technical Information

Chemical composition

CaO	42.6%
Al ₂ O ₃	29.7%
SO ₃	24.9%

Physical properties

Appearance	White powder
Physical state	Solid
Odor	Odorless
Specific gravity	2.90 – 2.96 g/cm ³
Blaine fineness	6,000 or more g/cm ²
pH	11 - 13 (dissolved)
Water solubility	Partially soluble in water. Will solidify over a period of hours if moistened or wet

Physical Properties (of Mortar)

General properties (typical values)

- Quick hardening additive (QHA): DENKA SC-1, other CAC (Calcium aluminate cement)
- Retarding agent: DENKA SETTER D-200 for SC-1, Tartaric acid for CAC
- Sand: ISO sand
- Water: Tap water
- Base mix proportion; Binder/Sand = 1.0/1.5, Water/Binder = 0.30
- Length change; uniaxial confined method, cured in water at 20°C after 1 day

OPC	Binder		Retarding agent (QHAX%)	Flow with 25 drops (mm)	Handling time(min)	Compressive strength (MPa)		
	QHA					3 hours	6 hours	1 day
	Product	Ratio						
100	—	—	—	153	300	—	—	32.0
85	SC-1	15	0.39	229	28	17.9	21.5	53.8
80		20	0.52	233	29	29.2	34.1	57.9
75		25	0.62	239	27	34.6	43.7	59.9
80	CAC	20	0.11	187	29	6.8	8.3	11.8
20		80	0.27	162	30	5.1	18.4	55.2
10		90	0.13	168	30	19.6	43.5	59.5

Handling Precautions

- Refer to the Safety Data Sheet (SDS) before use.
- Wear protective gear (goggles, mask, gloves, and rubber boots) while handling the product. Do not dispose of the product in drains.
- Once opened, the product should be used up completely. Otherwise, reseal for storage.
- The product should be stored in a dry area, indoors, and out of direct sunlight.
- For further information, please contact DENKA.

Limitation of Liability

- The information contained in this brochure provides general advice for potential customers of DENKA about the basic properties and characteristics of various DENKA products (hereafter referred to as "the Product Information"). DENKA makes no warranty or representation as to the entire accuracy or completeness of the Product Information in this brochure.
- Nothing in this brochure will be deemed to create any express or implied warranty or obligation of DENKA with respect to the Product Information or its use, including, but not limited to, any warranty of merchantability, fitness for a particular purpose, or infringement of any intellectual property rights.
- Each user of the Product Information and DENKA products assumes their own responsibility to properly determine the manner and suitability of use of the Product Information and DENKA products in its own operations. The user should exercise proper care in considering the Material Safety Data Sheet, Product Information and any other technical information provided by DENKA, including descriptions of the conditions of use, warnings, and other cautionary instructions.
- DENKA reserves the right to change the Product Information from time to time at its discretion and without notice.

Denka
<http://www.denka.co.jp/eng/>

Denka Co. Ltd.

Special Cement Additives Department
 TEL: +81-3-3507-5465 FAX: +81-3-3507-5085

-China-
DENKA INFRASTRUCTURE TECHNOLOGIES SHANGHAI

ROOM 2807, NEW HONGQIAO CENTER BLDG
 NO.83 LOUSHANGUAN RD, CHANG NING AREA, SHANGHAI CHINA
 TEL: +86-21-6236-5510
 FAX: +86-21-6236-5505

-Asia-
DENKA INFRASTRUCTURE TECHNOLOGIES PTE LTD

8 JURONG TOWN HALL ROAD #07-01
 THE JTC SUMMIT SINGAPORE 609434
 TEL: +65-6216-0580
 FAX: +65-6224-3840

DENKA CONSTRUCTION SOLUTIONS MALAYSIA SDN BHD

No.18, Jalan Utas 15/7, Seksyen 15,
 40200 Shah Alam, Selangor Darul Ehsan,
 Malaysia
 TEL: +603-5510-8810
 FAX: +603-5518-8202

-Europe-
DENKA CHEMICALS GMBH

WEHRHAHN-CENTER, CANTADOR STR.3,
 DUSSELDORF, GERMANY
 TEL: +49-211-130990
 FAX: +49-211-329942